



Automotive Aftermarket Division

3M 36105/36106/36107 Perfect-itTM Gelcoat Medium Cutting Compound + Wax

1) Part Numbers

36105	:	473ml
36106	:	946ml
36107	:	3.6l

2) Description and end uses

3MTM Perfect-ItTM Gelcoat Medium Cutting Compound + Wax is designed to remove P800 and finer sand scratches with a 3MTM compounding pad. It is designed to work over a broad range of climates. Its non-gritty formula works on all types of gelcoat surfaces, leaving an extremely fine finish with easy clean up. To reduce compounding time refine sanding marks with 3MTM TrizactTM 1500 before compounding.

3) Physical Properties

Container	Various (See Above)
Colour	White
Flash Point - °C	No Flash @ 20°C, 38°C, 60°C or 93°C
Viscosity (CPS) Brookfield Viscometer	30,000 – 40,000 cps @ 25°C
Solids Content (Appx.)	Trade Secret
Solvent	14.5% VOC



4) Directions for Use

Compound between 1200 and 2000 rpm using a buffer equipped with a 3M™ wool or 3M™ foam compounding pad.

1. Apply enough material to work a 2` x 2` area with a thin film throughout the buffing process. The product is designed to be used wet and buffed with a thin film. Important: If too much compound is applied to the surface, product may create a heavy film that reduces workability. If this occurs, remove excess material from both panel and pad surfaces. Spur buffing pad as necessary.
2. Start buffing with medium pressure between 1200 and 2000 rpm. For optimal finish, as the product begins to dry, reduce pressure at end of buffing cycle. Product can be buffed or wiped dry.
3. Use a soft cloth to remove any residual film and/or sling before moving on to another panel or before polishing.

5) Storage

Keep from freezing.

6) Safety

Refer to product label and safety data sheet for health and safety information before using the product.

7) Disclaimer

All statements, technical information and recommendations are based on tests we believe to be reliable but the accuracy or completeness thereof is not guaranteed. Please ensure before using our product that it is suitable for your intended use. All questions of reliability relating to this product are governed by the Terms of Sale subject, where applicable, to the prevailing law.



Technical Data Sheet

Effective: 04/05/2017

For Additional Health and Safety Information

Denmark

3M a/s
Automotive Aftermarket
Hannemanns Allé 53
2300 København S
Tel: 43 48 01 00
3mkundeservicedk@mmm.com
www.3MAuto.dk

Norway

3M Norge AS
Automotive Aftermarket
Kanalveien 2
2004 Lillestrøm
Telefon: 06384
www.3m.no/auto
kundeservice@mmm.com

Finland

Suomen 3M Oy
Automotive Aftermarket
Keilaranta 6
02150 Espoo
Tel: 09 5252 1
tilaukset@mmm.com
www.3M.fi/autotuotteet

Sweden

3M Svenska AB
Automotive Aftermarket
Bileftermarknad
19189 Sollentuna
Tel. 08-922100
kundservice@mmm.com
3M.se/bileftermarknad